

NEXA PU CLASSIC

Liquid polyurethane membrane for waterproofing and protection

Description:

Liquid polyurethane membrane for waterproofing and protection. Single-component product that cures through ambient air humidity, forming a continuous and elastic membrane with excellent mechanical and adhesion properties, making it resistant to weathering, extreme temperatures, and chemicals.

Approved Uses

Waterproofing and protection of:

- Inaccessible roofs or decks, limited to maintenance (Terraces, balconies, and roofs made of metal, aluminum, or fiber-cement...).
- Heavy-duty protected weight-bearing roofs (Bridge platforms and cement surfaces...).
- Roofs with adhesive coatings (Bathrooms, kitchens, and wet areas).
- Walkable roofs or decks (Terraces, balconies...).
- Roofs with heavy traffic (Parking lots, stations, stadium stands, shopping centers, etc.).
- Retention tanks (Water tanks and irrigation systems...).
- Green roofs.
- Underground structures.
- Asbestos encapsulation and protection, preventing the migration of asbestos particles.

Supported Substrates

Concrete, cement, mosaic, fiber-cement, tiles, acrylics restoration and asphalt emulsions, EPDM, wood, rusted metals, galvanized steel.

Advise: For other substrates, tests should be conducted to verify adhesion.

For specific details or conditions on special substrates, please contact the technical department.

Advantages

- Easy application.
- Excellent adhesion.
- Adapts to any surface shape.
- Allows restoration avoiding demolition or overweight.
- Easy detection and repair of ruptures.
- High resistance to weathering and UV.
- Excellent resistance to extreme temperatures (-40°F to $+176^{\circ}\text{F}$).
- Shock temperature of 392°F .
- High resistance to abrasion and tension.
- Great elasticity $>600\%$.
- Suitable for continuous contact with water, hydrolysis, and microorganisms.
- High chemical resistance.
- Once cured, the membrane is non-toxic.
- Allows vapor diffusion.



Application

- Requires a smooth, clean, dry surface without residual moisture and as solid as possible.
- Use a flexible two-component mortar for waterproofing or a single-component concrete repair mortar to adapt to irregular or defective substrates.
- Can be applied with a roller, brush, or airless spray gun.
- In case of dilution, apply only solvent in a maximum proportion of 10%.
- Best mixing the contents with a low-speed electric mixer.
- For single-layer applications, use a notched trowel with serrations of about 0.11", a defoamer and an accelerator. Pot life with an accelerator is approximately 30 minutes.
- Recoating time is between 6-24 hours, or about 3-4 hours when using an accelerator.
- Recoating should be done before 48 hours. If exceeded, NEXA PRIMER PU 2K should be used.
- Use a primer suitable for the substrate. Allow it to dry completely before application (Approx. 4 hours).
- Reinforce specific points, substrates with significant movement, active cracks, etc.
- To increase abrasion resistance and have a walkable pavement system or to enhance UV resistance (avoiding yellowing, chalking, or color changes), apply pigmented NEXA UV PROTECTIVE.
- Not suitable for application in swimming pools or reservoirs with treated water.
- Once opened, we recommend using the entire content.

NEXA PU CLASSIC

Liquid polyurethane membrane for waterproofing and protection

- We recommend reinforcing with reinforcement (EPDM tape reinforced with polyester fabric for specific points such as angles, expansion joints, active cracks, and insulation joints) or mastic (see NEXA MASTIC PU).
- For a slip-resistant application, add white corundum to the final layer of NEXA UV PROTECTIVE (varying its particle size according to the final use).

Cleaning

- Clean tools and equipment with a solvent.

Presentation and Colors

Metal containers of 55.115 lbs and boxes of 4 units of 13.228 lbs.

White (RAL 9010), Gray (RAL 7040), Tile, Green (RAL 6021), Beige (RAL 1014 and RAL 1015).

Container Stability

12 months in a dry place between 41°F to 77°F.

Transportation, Preventive measures and Storage

Refer to the safety data sheet.

The information provided serves as a recommendation based on laboratory tests and our current knowledge. Different conditions on construction sites may result in variations from the given information; therefore, our warranty is limited to the supplied product. For any questions, please contact our technical department.

Technical data of the membrane

CONCEPTS	RESULTS
Service temperature	-40°F to 175°F
Shock temperature	392°F
Hardness	Shore A / 70
Tensile strength at 73°F	800 psi
Elasticity percentage at 73°F	>600%
Water vapor transmission resistance	0.09 lb/ft ² -MTH
Fatigue motion resistance	Pass
Adhesion to concrete	>290 psi
QUV Weathering Resistance Test	Passes 200h
Thermal resistance (100 days at 175°F)	Pass
Hydrolysis (H ₂ O, 30 days - cycle 60 - at 60 to 212°F)	Without significant changes in elastomeric properties
Hydrolysis (8% KOH, 15 days at 120°F)	
HCl (PH=2, 10 days at RT)	
Estimated minimum lifecycle	W3 / 25 years
Climate zone	S / Severe
Roof slope	S1-S4 / <5% > 30%
Minimum substrate temperature	TL3 / -4°F
Maximum substrate temperature	TH1-TH4 / 86°F to 194°F
Usage loads	P1 / P4

Technical data of the liquid product

CONCEPTS	RESULTS
Viscosity	3000-6000 cSt
Specific weight	0.04 -0.05 lb/in
Flash Point	108°F
Recoat time	6-24 hours
Surface dry time at 77°F and 55% RH	6 hours
Solid content	95%



* laboratories working with us.

For more information about our products and systems, as well as technical documentation downloads or safety data sheets, please visit our website or contact us.

NEXA COATINGS
 contact@nexacoatings.com
 +1 3052304789 www.nexacoatings.com